



Product Data Sheet

Carton Sealing Tape Acrylic Solvent Based Adhesive (36XX)

Carton Sealing Tape Acrylic Solvent Based Adhesive (36XX)

Polypropylene Carton Sealing Tap, ACRYLIC SOLVENT BASED ADHESIVE

3622 - Clear & Tan

- 2.2 mil (0.055mm). 28 micron film. A biaxially oriented polypropylene tape, coated with a Solvent Based Acrylic Adhesive.
- Adhesion: 23 oz/in.
- Tensile: 20 lbs/in.
- Elongation at break: 140%.
- Temp. resistance: 35°F to 150°F. 3? neutral core/carton.
- 49? (1260mm) x 4000M Length Jumbo Rolls

3626 - Clear & Tan

- 2.7 mil (0.068mm). 40 micron film. A biaxially oriented polypropylene tape, coated with a Solvent Based Acrylic Adhesive
- Adhesion: 27 oz/in.
- Tensile: 24 lbs/in.
- Elongation at break: 140%.
- Temp. resistance: 35°F to 150°F.
- Great balance of adhesion and tensile strength for heavy weight carton sealing applications. 3? neutral core/carton. Meets SPEC. A-A-1684C.

3634 - Clear & Tan

- 3.6 mil (0.09mm). 60 micron film. A biaxially oriented polypropylene tape, coated

NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith.

All test procedures used are in accordance with ASTM and PSTC methods.

with a PREMIUM GRADE Solvent Based Acrylic Adhesive.

- Adhesion: 33 oz/in.
- Tensile: 38 lbs/in.
- Elongation at break: 200%.
- Temp. resistance: 32°F to 150°F.

Its strong adhesion to cardboard and high tensile strength makes it an excellent choice for extremely demanding packaging needs. 3" neutral core/carton.

NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.