



# Product Data Sheet

## Color Carton Sealing Tape 2.0 Mil (6120)



NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.

**[tapedepot.com](http://tapedepot.com) | [support@tapedepot.com](mailto:support@tapedepot.com) | 888.282.8273**

2020-05-27 02:53:49 172.31.87.187

## **Color Carton Sealing Tape (6120)**

(COLORED POLYPROPYLENE TAPE with WATER BASED ACRYLIC ADHESIVE)

8 Colors: White, black, yellow, red, purple, green, orange, and blue.

### **DESCRIPTION:**

Colored Carton Sealing Tape is a moderate strength biaxially oriented Polypropylene tape coated with a water based Acrylic adhesive. Good balance of adhesion and strength for a wide range of carton sealing and identification applications.

### **APPLICATIONS:**

Used for carton sealing, color coding, general purpose splicing, tabbing and identification.

### **PHYSICAL PROPERTIES:**

- Backing: Polypropylene (28 micron)
- Adhesive: Water Based Acrylic Adhesive
- Total Thickness: 2.0 mil (0.048mm)
- Adhesion to SST: 22 oz/inch
- Tensile Strength: 18 lb/inch
- Elongation: ? 180%
- Temperature Range: 32°F to 140°F

### **STORAGE TEMPERATURE AND SHELF LIFE:**

Tape should be stored in a cool, dry area at temperatures of 60°F to 80°F. If stored appropriately, expected shelf life of up to 1 year from date of manufacturer/conversion.

NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.