



Product Data Sheet

Polyethylene Film Tape 7 Mil UV 60 Yd (63535)

Polyethylene Adhesive Tape is 4.5 mil low-density polyethylene film tape coated on one side with a synthetic rubber adhesive.

Backing has been stabilized with additives to resist the effects of UV exposure. Leaves no residue on removal and maintains a watertight seal in all weather conditions. Its adhesive system remains permanently tacky and bonds well to most surfaces over a wide range of temperatures. 3" paper core.

Applications:

Designed for masking of windows and doors in stucco applications. Ideal for polyethylene splicing or seaming in construction applications.

Physical Properties:

Total Thickness: 7.0 Mil (0.178mm)

Film: 4.5 Mil

Adhesive: Synthetic Rubber

Tensile Strength: 18 lbs/in.

Elongation: Peel adhesion

Peel Adhesion: 60 oz/in.

Adhesion to backing: 35 oz/in.

2 COLORS AVAILABLE: Red & White.
NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use, and user assumes all risks and liabilities in connection therewith. Alternative to Scapa #234 & Berry Plastics Red Baron; Permaceel #224LB; Gantech #250.
test procedures used are in accordance with ASTM and PSTC methods.

tapedepot.com | support@tapedepot.com | 888.282.8273

2023-03-30 08:34:31 172.31.87.187

Note: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.

NOTE: The physical properties listed above are typical test results obtained from a series of laboratory tests and should not be used for the purpose of writing specifications. Before using this product, user shall determine the suitability of the product for his/her use; and user assumes all risks and liabilities in connection therewith. All test procedures used are in accordance with ASTM and PSTC methods.

tapedepot.com | support@tapedepot.com | 888.282.8273

2023-03-30 08:34:31 172.31.87.187